

## Veradel<sup>®</sup> 3000P

## polyethersulfone

Veradel<sup>®</sup> 3000P, 3100P, 3200P, 3400P and 3600P are polyethersulfone (PESU) powders for dissolving or dispersing into solutions. They can also be ground to smaller particle size or blended with other solid particles. The grades differ by their molecular weights, with 3000P the highest and 3600P the lowest. There is a direct correlation between molecular weight and solution viscosity.

PESU offers excellent toughness and outstanding hydrolytic resistance. It resists attack from steam,

boiling water, and mineral acids. Cast films or coatings of PESU are transparent and have additional desirable properties including long term thermal stability, excellent metal adhesion and formability and inherent flame resistance.

Typical applications include high-temperature coating formulations, membranes, advanced hightemperature composites, and specialty adhesives.

This grade was formerly marketed as Gafone™ PESU

General				
Material Status	<ul> <li>Commercial: Active</li> </ul>			
Availability	<ul> <li>Africa &amp; Middle East</li> <li>Asia Pacific</li> <li>Europe</li> </ul>	_	atin America Iorth America	
Features	<ul> <li>Acid Resistant</li> <li>Chemical Resistant</li> <li>Creep Resistant</li> <li>Flame Retardant</li> <li>Food Contact Acceptabl</li> <li>Good Adhesion</li> <li>Good Dimensional Stabil</li> <li>Good Thermal Stability</li> </ul>	• H • H • H • H • H	Good Toughness ligh Heat Resist ligh Molecular V ligh Tensile Stre lydrolysis Resist ow Flow 1edium Rigidity	ance Weight ength tant
Uses	<ul> <li>Membranes</li> </ul>			
Agency Ratings	• NSF STD-61 <sup>1</sup>			
RoHS Compliance	<ul> <li>Contact Manufacturer</li> </ul>			
Appearance	<ul> <li>Transparent - Slight Yella</li> </ul>	w		
Forms	• Powder			
Processing Method	• Cast Film • Coating	<ul><li>Solution Processing</li><li>Spraying</li></ul>		
Physical		Typical Value	Unit	Test method
Density / Specific Gravity		1.37		ASTM D792
Water Absorption (24 hr)		0.60	%	ASTM D570
Solution Viscosity <sup>2</sup>		1450	mPa∙s	Internal Method
Residual Solvent		0.50	%	Internal Method
Thermal		Typical Value	Unit	Test method
Glass Transition Temperature		220	°C	ASTM E1356
CLTE - Flow		4.9E-5	cm/cm/ºC	ASTM D696

## Notes

Typical properties: these are not to be construed as specifications.

- <sup>1</sup> Tested at 82 °C (180 °F) (Commercial Hot). Only products bearing the NSF Mark are Certified.
- $^{2}$  25% in dimethylacetamide at 40°C

## www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infinged. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.

