

Ajedium™ Films -- KetaSpire® KT-820 polyetheretherketone

KetaSpire® KT-820 PEEK film is thermoplastic film that is characterized by a distinct combination of properties, which include excellent wear resistance, best-in-class fatigue resistance, high purity, and excellent chemical resistance to organics, acids,

and bases. These properties make it well-suited for applications in aerospace, electronics, chemical processing, healthcare, transportation, and other industrial uses.

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Features	• Chemical Resistant • Ductile • Fatigue Resistant • Flame Retardant • Good Dimensional Stability	• Good Impact Resistance • Good Sterilizability • High Heat Resistance • Radiation (Gamma) Resistant
Uses	• Aircraft Applications • Automotive Applications • Electrical/Electronic Applications	• Industrial Applications • Medical/Healthcare Applications • Oil/Gas Applications
RoHS Compliance	• RoHS Compliant	
Appearance	• Translucent	

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.30		ASTM D792
Water Absorption (24 hr)	0.50	%	ASTM D570

Mechanical	Typical Value	Unit	Test method
Tear Resistance (125.0 µm)	10.0	cN	ASTM D1004

Films	Typical Value	Unit	Test method
Film Thickness - Tested			
--	25	µm	
-- 1	50	µm	
-- 2	130	µm	
Secant Modulus			ASTM D882
MD : 25 µm	2050	MPa	
MD : 150 µm ³	2680	MPa	
TD : 25 µm	2000	MPa	
TD : 150 µm ³	2540	MPa	

Ajedium™ Films -- KetaSpire® KT-820

polyetheretherketone

Films	Typical Value	Unit	Test method
Tensile Strength			ASTM D882
MD : Yield, 25 µm	75.8	MPa	
MD : Yield, 150 µm ³	74.5	MPa	
TD : Yield, 25 µm	72.4	MPa	
TD : Yield, 150 µm ³	71.7	MPa	
MD : Break, 25 µm	109	MPa	
MD : Break, 150 µm ³	124	MPa	
TD : Break, 25 µm	95.8	MPa	
TD : Break, 150 µm ³	123	MPa	
Tensile Elongation			ASTM D882
MD : Yield, 25 µm	6.8	%	
MD : Yield, 150 µm ³	5.5	%	
TD : Yield, 25 µm	6.7	%	
TD : Yield, 150 µm ³	5.4	%	
MD : Break, 25 µm	150	%	
MD : Break, 150 µm ³	190	%	
TD : Break, 25 µm	170	%	
TD : Break, 150 µm ³	210	%	
Dart Drop Impact (50 µm)	1300	g	ASTM D1709B
Area Factor	149	ft ² /lb/mil	
Tear Propagation Resistance (125.0 µm)	320	gf	ASTM D1922
Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load ⁴			ASTM D648
1.8 MPa, Annealed, 3.20 mm	157	°C	
Glass Transition Temperature	150	°C	ASTM D3418
Peak Melting Temperature	340	°C	ASTM D3418
CLTE - Flow (-50 to 50°C)	4.3E-5	cm/cm/°C	ASTM E831
Thermal Conductivity	0.24	W/m/k	ASTM E1530
Electrical	Typical Value	Unit	Test method
Surface Resistivity	> 1.9E+17	ohms	ASTM D257
Volume Resistivity	2.6E+16	ohms·cm	ASTM D257
Dielectric Strength (0.0500 mm)	150	kV/mm	ASTM D149
Dielectric Constant (1 kHz)	3.10		ASTM D150
Flammability	Typical Value	Unit	Test method
Oxygen Index	37	%	ASTM D2863

Ajedium™ Films -- KetaSpire® KT-820

polyetheretherketone

Additional Information

Standard Thicknesses and Widths

- Widths are available from 22" (559 mm) to 56" (1422 mm).
- Products with widths <22 inches or >56 inches are available upon request.
- Tolerances for widths are \pm 4mm.
- For KetaSpire® film, the standard thicknesses are 8 microns (0.3 mil) to 1016 microns (40 mil).

Surface Finishes

- Standard surface finish is P/M (polished / matte).
- Custom finishes of P/P (polished / polished) and M/M (matte / matte) are available.

Packaging

- Film is supplied in a roll form of high quality, cardboard core of 3" (76mm) or 6" (152mm).
- PVC cores are available upon request in 3" and 6" sizes.

Labeling

- Products are labeled to comply with national and international standards.
 - Labels include product grade, unique batch number, roll length, roll width, product thickness, and net weight.
-

Notes

Typical properties: these are not to be construed as specifications.

¹ Impact properties

² Tear properties

³ 51 mm/min

⁴ 2 hours at 200°C

www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.

