

Amodel® A-4122 HR WH 117

polyphthalamide

Amodel® A-4122 HR resin is a 22% glass reinforced polyphthalamide (PPA), designed to provide high crystallinity when molded in water-cooled molds. This material exhibits high heat resistance, high strength and stiffness over a broad temperature range, low moisture absorption, excellent chemical

resistance, and excellent electrical properties. Its rapid crystallization rate and high flow can result in short cycles and therefore high molding productivity and lower part cost.

- White: A-4122 HR WH 117

General

Material Status	• Commercial: Active
Availability	<ul style="list-style-type: none"> • Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Filler / Reinforcement	• Glass Fiber, 22% Filler by Weight
Features	<ul style="list-style-type: none"> • Chemical Resistant • Fast Molding Cycle • Good Color Stability • High Reflectivity • Low Moisture Absorption
Uses	<ul style="list-style-type: none"> • Automotive Applications • Automotive Electronics
RoHS Compliance	• RoHS Compliant
Appearance	• White
Forms	• Pellets
Processing Method	• Water-Heated Mold Injection Molding

Physical	Typical Value	Unit	Test method
Density	1.50	g/cm ³	ISO 1183/A
Molding Shrinkage			ASTM D955
Flow	0.40	%	
Across Flow	0.60	%	
Water Absorption (24 hr)	0.24	%	ASTM D570

Mechanical	Typical Value	Unit	Test method
Tensile Modulus	9100	MPa	ISO 527-1
Tensile Stress (Yield)	125	MPa	ISO 527-2
Tensile Strain (Break)	1.5	%	ISO 527-2
Flexural Modulus	7790	MPa	ISO 178
Flexural Stress	171	MPa	ISO 178

Impact	Typical Value	Unit	Test method
Notched Izod Impact			
--	27	J/m	ASTM D256
--	2.5	kJ/m ²	ISO 180/1A

Amodel® A-4122 HR WH 117

polyphthalamide

Hardness	Typical Value	Unit	Test method
Rockwell Hardness (R-Scale)	124		ASTM D785

Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load 0.45 MPa, Unannealed	318	°C	ISO 75-2/B
Melting Temperature	321	°C	ISO 11357-3
CLTE			ASTM E831
Flow : 0 to 100°C	3.1E-5	cm/cm/°C	
Flow : 150 to 250°C	1.4E-5	cm/cm/°C	
Transverse : 0 to 100°C	7.4E-5	cm/cm/°C	
Transverse : 150 to 250°C	1.6E-4	cm/cm/°C	

Additional Information	Typical Value	Unit	Test method
Optical Reflectivity ¹	> 90	%	ASTM E1331

Injection	Typical Value	Unit
Drying Temperature	120	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.030 to 0.060	%
Rear Temperature	304 to 318	°C
Front Temperature	316 to 329	°C
Processing (Melt) Temp	321 to 343	°C
Mold Temperature	135	°C

Injection Notes

Storage:

- Amodel® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Amodel® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Amodel® processing guide.

Notes

Typical properties: these are not to be construed as specifications.

¹ 430 – 700 nm

Amodel® A-4122 HR WH 117

polyphthalamide



www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.