

# Amodel® AE-4133

## polyphthalamide

Amodel® AE-4133 is a 33% glass reinforced, hot-water moldable polyphthalamide (PPA) designed to work in the modern automotive electrical environment.

This grade features a high heat deflection temperature, high flexural modulus and high tensile

strength, as well as excellent creep resistance and low moisture absorption.

- Black: AE-4133 BK902
- Natural: AE-4133 NT

### General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Glass Fiber, 33% Filler by Weight	
Features	• Chemical Resistant • Creep Resistant • Good Dimensional Stability • Good Stiffness • High Heat Resistance	• High Stiffness • High Strength • High Temperature Strength • Low Moisture Absorption
Uses	• Automotive Electronics • Connectors	• Electrical Parts • Electrical/Electronic Applications
RoHS Compliance	• Contact Manufacturer	
Appearance	• Black	• Natural Color
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Dry	Conditioned	Unit	Test method
Density	1.45	--	g/cm <sup>3</sup>	ISO 1183/A
Molding Shrinkage				ASTM D955
Flow	0.40	--	%	
Across Flow	0.80	--	%	
Water Absorption (24 hr)	0.23	--	%	ASTM D570

Mechanical	Dry	Conditioned	Unit	Test method
Tensile Modulus (23°C)	12000	--	MPa	ISO 527-1
Tensile Stress (Break, 23°C)	210	--	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.5	--	%	ISO 527-2
Flexural Modulus (23°C)	10700	--	MPa	ISO 178
Flexural Stress (23°C)	295	--	MPa	ISO 178
Flexural Strain	3.1	--	%	ISO 178

# Amodel® AE-4133

## polyphthalamide

Impact	Dry	Conditioned	Unit	Test method
Charpy Notched Impact Strength (23°C)	9.0	--	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	79	--	kJ/m <sup>2</sup>	ISO 179/1eU
Notched Izod Impact Strength (23°C)	9.2	--	kJ/m <sup>2</sup>	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	68	--	kJ/m <sup>2</sup>	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test method
Deflection Temperature Under Load 1.8 MPa, Unannealed	> 300	--	°C	ISO 75-2/A
Glass Transition Temperature	95.0	--	°C	DSC
Melting Temperature	327	--	°C	ISO 11357-3
CLTE				ASTM E831
Flow : 0 to 100°C <sup>1</sup>	2.0E-5	--	cm/cm/°C	
Flow : 100 to 200°C <sup>2</sup>	1.5E-5	--	cm/cm/°C	
Transverse : 0 to 100°C <sup>3</sup>	7.6E-5	--	cm/cm/°C	
Transverse : 100 to 200°C <sup>4</sup>	1.2E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test method
Volume Resistivity	5.6E+15	5.0E+14	ohms·cm	ASTM D257
Dielectric Strength (3.20 mm)	19	19	kV/mm	ASTM D149 IEC 60243-1
Dielectric Constant				ASTM D150 IEC 60250
60 Hz	4.10	4.30		
1 MHz	3.75	3.40		
Dissipation Factor				ASTM D150 IEC 60250
60 Hz	6.0E-3	0.020		
1 MHz	0.015	0.019		
Comparative Tracking Index (CTI)	600	600 V		UL 746A
Comparative Tracking Index	600	600 V		IEC 60112
High Voltage Arc Tracking Rate (HVTR)	14.0	18.0 mm/min		UL 746A
Flammability	Dry	Conditioned	Unit	Test method
Flame Rating <sup>5</sup> (3.2 mm)	HB	--		UL 94

# Amodel® AE-4133

## polyphthalamide

Injection	Dry Unit
Drying Temperature	120 °C
Drying Time	4.0 hr
Suggested Max Moisture	0.030 to 0.060 %
Rear Temperature	320 to 330 °C
Middle Temperature	320 to 330 °C
Front Temperature	327 to 335 °C
Processing (Melt) Temp	330 to 345 °C
Mold Temperature <sup>6</sup>	90 to 100 °C

### Injection Notes

Injection Rate: 3-4 inch/second (7.5-10 cm/sec)  
Holding Pressure: 50% of injection pressure

### Storage:

- Amodel® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Amodel® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Amodel® processing guide.

## Notes

Typical properties: these are not to be construed as specifications.

- <sup>1</sup> This is equivalent to 0.20EE-04 /°K by ISO 11359
- <sup>2</sup> This is equivalent to 0.15EE-04 /°K by ISO 11359
- <sup>3</sup> This is equivalent to 0.76EE-04 /°K by ISO 11359
- <sup>4</sup> This is equivalent to 0.12EE-04 /°K by ISO 11359
- <sup>5</sup> These flammability ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.
- <sup>6</sup> Note that higher mold temperatures may be necessary for very thin-walled parts, or to achieve better quality surface finish.



**www.syensqo.com**

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.