

AvaSpire® AV-742 SL30 polyaryletherketone

AV-742 SL30 is a wear resistant grade of AvaSpire® polyaryletherketone (PAEK) designed to provide low wear rates in both non-lubricated and lubricated environments. In addition to outstanding wear resistance, the resin also offers the outstanding combination of ultra-performance attributes commonly known for PEEK. These include: chemical resistance, mechanical strength and stiffness, even at elevated temperatures, as well as long-term and high-temperature thermal-oxidative stability. AV-742 SL30 is formulated with the ternary anti-friction/anti-wear additive system comprised of carbon fiber, graphite, and polytetrafluoroethylene (PTFE). It offers wear resistance performance comparable to PEEK grades with this modifier system while being more cost-effective.

This high flowing (low viscosity) grade is designed for use in the injection molding of thin, intricate or

complex shapes, or parts in otherwise challenging molding configurations. If the part geometry is such that low viscosity is not a processing necessity, it is recommended that the companion grade AV-722 SL30 be considered first to take advantage of the higher molecular weight of that grade, which results in greater wear resistance as well as better overall mechanical performance in terms of toughness-related properties. The resin can be melt processed using conventional equipment and techniques.

Potential applications for AV-742 SL30 include bushings, bearings, wear strips, wear rings, rollers, and other parts used in sliding friction components. The resin is black in color in its natural state.

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Additive	• Carbon Fiber + Graphite + PTFE Lubricant	
Features	• Chemical Resistant • Flame Retardant • Good Dimensional Stability	• High Heat Resistance • Wear Resistant
Uses	• Automotive Applications • Bushings	• Thin-walled Parts • Wear Strip
RoHS Compliance	• Contact Manufacturer	
Appearance	• Black	
Forms	• Pellets	
Processing Method	• Injection Molding • Machining	• Profile Extrusion

AvaSpire® AV-742 SL30

polyaryletherketone

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.47		ASTM D792
Melt Mass-Flow Rate (MFR) (400°C/2.16 kg)	2.5	g/10 min	ASTM D1238
Molding Shrinkage ¹			ASTM D955
Flow : 3.18 mm	0.10 to 0.30	%	
Across Flow : 3.18 mm	1.6 to 1.8	%	
Water Absorption (24 hr)	0.030	%	ASTM D570
Mechanical	Typical Value	Unit	Test method
Tensile Modulus			
-- ²	13000	MPa	ASTM D638
--	15500	MPa	ISO 527-1/1A/1
Tensile Stress			
Yield	156	MPa	ISO 527-2/1A/5
-- ²	143	MPa	ASTM D638
Tensile Elongation			
Break ²	1.8	%	ASTM D638
Break	1.8	%	ISO 527-2/1A/5
Flexural Modulus			
--	10400	MPa	ASTM D790
--	13200	MPa	ISO 178
Flexural Strength			
--	211	MPa	ASTM D790
--	203	MPa	ISO 178
Compressive Strength	121	MPa	ASTM D695
Shear Strength	70.0	MPa	ASTM D732
Impact	Typical Value	Unit	Test method
Notched Izod Impact			
--	53	J/m	ASTM D256
--	5.8	kJ/m ²	ISO 180
Unnotched Izod Impact			
--	410	J/m	ASTM D4812
--	28	kJ/m ²	ISO 180
Hardness	Typical Value	Unit	Test method
Rockwell Hardness (M-Scale)	87		ASTM D785

AvaSpire® AV-742 SL30
polyaryletherketone

Thermal	Typical Value Unit	Test method
Deflection Temperature Under Load 1.8 MPa, Annealed	276 °C	ASTM D648
Glass Transition Temperature	152 °C	ASTM D3418
Peak Melting Temperature	343 °C	ASTM D3418
CLTE - Flow (-50 to 50°C)	1.0E-5 cm/cm/°C	ASTM E831
Specific Heat		DSC
50°C	1250 J/kg/°C	
200°C	1710 J/kg/°C	
Thermal Conductivity	0.34 W/m/K	ASTM E1530

Fill Analysis	Typical Value Unit
Melt Viscosity (400°C, 1000 sec ⁻¹)	270 Pa·s

Injection	Typical Value Unit
Drying Temperature	149 °C
Drying Time	4.0 hr
Rear Temperature	354 °C
Middle Temperature	366 °C
Front Temperature	371 °C
Nozzle Temperature	374 °C
Processing (Melt) Temp	366 to 388 °C
Mold Temperature	149 to 177 °C
Injection Rate	Fast
Screw Compression Ratio	2.0:1.0 to 3.0:1.0

Notes

Typical properties: these are not to be construed as specifications.

¹ 5" x 0.5" x 0.125" bars

² 5.0 mm/min



www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.