

## Diofan® F 807

### polyvinylidene chloride

Breakers are an important component of gelled hydraulic fracturing fluids as they assist with clean-up of the fracture when the pressure is released. Diofan® grade F 807 is a low foaming PVDC dispersion grade which offers superior performance attributes making it ideal for encapsulating breaking agents such as ammonium, potassium and sodium persulphate.

- Stable fine particle dispersion to ensure good colloidal stability under shear encountered at the spray nozzle
- Very low viscosity suitable for spray coaters
- Low foaming with excellent surface wettability and coating coverage
- Allow non-tacky and slip resistant coatings to maximize process output

These attributes include:

- Good coverage and pin-hole free coatings

#### General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Features	• Dispersible	• Low Viscosity
Uses	• Coating Applications	• Encapsulant
Agency Ratings	• AICS Listed on Inventory • DSL Listed on Inventory • EC 1907/2006 (REACH)	• EINECS Listed on Inventory • TSCA Listed on Inventory
Appearance	• Milky White	
Forms	• Liquid	

#### Physical

#### Typical Value Unit

Density		
Coated film (dry)	1.65 g/cm³	
Dispersion (wet)	1.33 g/cm³	
Emulsion Type	Anionic	
Filmability - Film Forming Temperature	8 to 14 °C	
pH	2.2	
Solids Content	60 %	
Surface Tension - Foaming tendency	54 mN/m	

#### Mechanical

#### Typical Value Unit

#### Test method

Coefficient of Friction		ASTM D1894
vs. Itself - Dynamic	0.30	

#### Additional Information

#### Typical Value Unit

Barrier Properties - Water, Cobb test for 30 minutes (80°C, 37.0 µm)	0.2 g/m²	
Shelf Life (23°C)	12 month	

# Diofan® F 807

## polyvinylidene chloride

---

### DELIVERY AND STORAGE

- Diofan® F 807 is delivered in bulk or in Intermediate Bulk Containers (IBC). Bulk supplied latex should be stored in reservoirs made of suitable stainless steel, HDPE, rigid PVC or glass fiber-reinforced polyester.
- Contact of anionic Diofan® dispersions with metals like iron, zinc, aluminum and copper as well as alloys such as brass and bronze must be avoided.
- Keep the vessels tightly closed to prevent drying through evaporation. Store the product ideally between 5°C and 30°C (41 °F and 86°F) to avoid degradation.

### PROCESSING - DRYING

- Diofan® F 807 can be processed with different coating techniques, including industrial spray coating processes.
- Diofan® coatings require adequate drying conditions, since, in general, higher temperatures will contribute to better barrier properties.

### FOOD AND DRUG LEGISLATIONS

- Some agency ratings are listed on page 1. Necessary certification will be provided upon request.

### ISO CERTIFICATION

- The implemented management system for the production, internal transfer and delivery, design and development of Diofan® vinylidene chloride copolymers (PVDC) produced in Tavaux has been assessed and found to meet the requirements of ISO 9001:2008, ISO 14001:2004 and OHSAS 18001:2007.

---

## Notes

Typical properties: these are not to be construed as specifications.

---

**[www.syensqo.com](http://www.syensqo.com)**

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.

