

Halar® 300DA

ethylene chlorotrifluoroethylene copolymer

General

| | | |
|-------------------|--|------------------------------------|
| Material Status | • Commercial: Active | |
| Availability | • Africa & Middle East • Asia Pacific • Europe | • Latin America • North America |
| Features | • Medium Viscosity | |
| Forms | • Pellets | |
| Processing Method | • Extrusion | • Injection Molding |

| Physical | Typical Value | Unit | Test method |
|---|---------------|----------|-------------|
| Density / Specific Gravity | 1.68 | | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (275°C/2.16 kg) | 2.0 | g/10 min | ASTM D1238 |
| Molding Shrinkage - Flow | 2.5 | % | ASTM D955 |
| Water Absorption (Equilibrium) | < 0.10 | % | ASTM D570 |

| Mechanical | Typical Value | Unit | Test method |
|---------------------------------------|---------------|------|-------------|
| Tensile Modulus ¹ (23°C) | 1660 | MPa | ASTM D638 |
| Tensile Strength ¹ | | | ASTM D638 |
| Yield, 23°C | 30.0 | MPa | |
| Break, 23°C | 54.0 | MPa | |
| Tensile Elongation ¹ | | | ASTM D638 |
| Yield, 23°C | 5.0 | % | |
| Break, 23°C | 250 | % | |
| Flexural Modulus ² (23°C) | 1690 | MPa | ASTM D790 |
| Flexural Strength ² (23°C) | 47.0 | MPa | ASTM D790 |
| Coefficient of Friction | | | ASTM D1894 |
| vs. Itself - Dynamic | 0.20 | | |
| vs. Itself - Static | 0.20 | | |

| Impact | Typical Value | Unit | Test method |
|---------------------|---------------|------|-------------|
| Notched Izod Impact | | | ASTM D256 |
| -40°C, 3.20 mm | 100 | J/m | |
| 23°C, 3.20 mm | No Break | | |

| Hardness | Typical Value | Unit | Test method |
|------------------------------|---------------|------|-------------|
| Rockwell Hardness (R-Scale) | 90 | | ASTM D785 |
| Durometer Hardness (Shore D) | 75 | | ASTM D2240 |

Halar® 300DA

ethylene chlorotrifluoroethylene copolymer

| Thermal | Typical Value Unit | Test method |
|--|--------------------|-------------|
| Deflection Temperature Under Load | | ASTM D648 |
| 0.45 MPa, Unannealed | 90.0 °C | |
| 1.8 MPa, Unannealed | 65.0 °C | |
| Brittleness Temperature | < -76.0 °C | ASTM D746A |
| Glass Transition Temperature | 85.0 °C | DMA |
| Melting Temperature | 242 °C | ASTM D3418 |
| Peak Crystallization Temperature (DSC) | 222 °C | ASTM D3418 |
| CLTE - Flow | 1.0E-4 cm/cm/°C | ASTM D696 |
| Specific Heat (23°C) | 962 J/kg/°C | ASTM D3418 |
| Thermal Conductivity (40°C) | 0.15 W/m/K | ASTM C177 |
| Crystallization Heat | 40.0 J/g | ASTM D3418 |
| Heat of Fusion | 42.0 J/g | ASTM D3418 |
| Thermal Stability - 1% mass loss, N2 | 405 °C | TGA |

| Electrical | Typical Value Unit | Test method |
|--|--------------------|-------------|
| Volume Resistivity ³ (23°C) | 5.5E+16 ohms·cm | ASTM D257 |
| Dielectric Strength (23°C, 3.20 mm) | 14 kV/mm | ASTM D149 |
| Dielectric Constant (23°C, 1 MHz) | 2.57 | ASTM D150 |

| Flammability | Typical Value Unit | Test method |
|--------------|--------------------|-------------|
| Flame Rating | V-0 | UL 94 |
| Oxygen Index | 52 % | ASTM D2863 |

Additional Information

Storage and Handling

- Halar® melt processable fluoropolymer resins can be stored without shelf life issues when kept in a clean and dry area at ambient temperatures. Opened containers should be tightly resealed to prevent any contamination.

Notes

Typical properties: these are not to be construed as specifications.

¹ 50 mm/min

² 2.5 mm/min

³ 50% RH



www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.