

Halar® 930LC

ethylene chlorotrifluoroethylene copolymer

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Features	• Medium Viscosity	
Forms	• Pellets	
Processing Method	• Extrusion	

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.68		ASTM D792
Melt Mass-Flow Rate (MFR) (275°C/2.16 kg)	4.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow	2.5	%	ASTM D955
Water Absorption (Equilibrium)	< 0.10	%	ASTM D570

Mechanical	Typical Value	Unit	Test method
Tensile Modulus ¹ (23°C)	1660	MPa	ASTM D638
Tensile Strength ¹			ASTM D638
Yield, 23°C	30.0	MPa	
Break, 23°C	54.0	MPa	
Tensile Elongation ¹			ASTM D638
Yield, 23°C	5.0	%	
Break, 23°C	250	%	
Flexural Modulus ² (23°C)	1690	MPa	ASTM D790
Flexural Strength ² (23°C)	47.0	MPa	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.20		
vs. Itself - Static	0.20		

Impact	Typical Value	Unit	Test method
Notched Izod Impact (23°C, 3.20 mm)	No Break		ASTM D256

Hardness	Typical Value	Unit	Test method
Rockwell Hardness (R-Scale)	90		ASTM D785
Durometer Hardness (Shore D)	75		ASTM D2240

Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	90.0	°C	
1.8 MPa, Unannealed	65.0	°C	

Halar® 930LC

ethylene chlorotrifluoroethylene copolymer

Thermal	Typical Value Unit	Test method
Brittleness Temperature	< -76.0 °C	ASTM D746A
Glass Transition Temperature	85.0 °C	DMA
Melting Temperature	242 °C	ASTM D3418
Peak Crystallization Temperature (DSC)	222 °C	ASTM D3418
CLTE - Flow	1.0E-4 cm/cm/°C	ASTM D696
Specific Heat (23°C)	962 J/kg/°C	ASTM D3418
Thermal Conductivity (40°C)	0.15 W/m/K	ASTM C177
Crystallization Heat	40.0 J/g	ASTM D3418
Heat of Fusion	42.0 J/g	ASTM D3418
Thermal Stability - 1% mass loss, N2	405 °C	TGA

Electrical	Typical Value Unit	Test method
Volume Resistivity ³ (23°C)	5.5E+16 ohms·cm	ASTM D257
Dielectric Strength (23°C, 3.20 mm)	14 kV/mm	ASTM D149
Dielectric Constant (23°C, 1 MHz)	2.57	ASTM D150

Flammability	Typical Value Unit	Test method
Flame Rating	V-0	UL 94
Oxygen Index	52 %	ASTM D2863

Additional Information

Storage and Handling

- Halar® melt processable fluoropolymer resins can be stored without shelf life issues when kept in a clean and dry area at ambient temperatures. Opened containers should be tightly resealed to prevent any contamination.

Notes

Typical properties: these are not to be construed as specifications.

¹ 50 mm/min

² 2.5 mm/min

³ 50% RH

www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.

