

Hyflon® PFA P7010

perfluoroalkoxy

Hyflon® PFA P7010 is a clear, semi-crystalline melt processable perfluorinated resin. It is designed for electrostatic powder coatings and is particularly recommended for use as a topcoat in antistick applications.

Hyflon® PFA P7010 exhibits very low surface energy, very low coefficient of friction and excellent thermal and flame resistance. Additionally Hyflon® PFA P7010 coatings show excellent smooth surface finish,

outstanding antistick behaviour and can maintain performance over a wide temperature range.

Main features of Hyflon® PFA P7010 include:

- Very low surface energy
- Excellent antistick behaviour
- Very low coefficient of friction
- Very good surface finish
- Outstanding thermal resistance

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Features	• Good Surface Finish • Good Thermal Stability	• Low Friction • Semi Crystalline
Uses	• Coating Applications	
Appearance	• Clear/Transparent	
Forms	• Powder	
Processing Method	• Coating	

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	2.16		ASTM D792
Melt Mass-Flow Rate (MFR) (372°C/5.0 kg)	10 to 17	g/10 min	ASTM D1238
Average Particle Size ¹	25	µm	Internal Method

Thermal	Typical Value	Unit	Test method
Melting Temperature	300 to 310	°C	ASTM D4591

Hyflon® PFA P7010

perfluoroalkoxy

Additional Information

Processing

- Hyflon® PFA P7010 is intended as a topcoat material to apply to primed substrates. It can be processed using normal electrostatic powder coating techniques. Generally the procedure involves substrate preparation, coating, baking and cooling.
- Hyflon® PFA P7010 can be used neat and without any further formulation. Several passes may be required to obtain the desired PFA load and build up coating thickness without defects.
- Substrate preparation, gun parameters such as voltage and both oven temperature and time must all be well controlled to achieve defect free coated items.

Storage and Handling

- Hyflon® melt processable fluoropolymer resins can be stored without shelf life issues when kept in a clean and dry area at ambient temperatures. Opened containers should be tightly resealed to prevent any contamination.

Safety and Toxicology

- Before using Hyflon® melt processable fluoropolymer resins consult the product Material Safety Data Sheet and follow all label directions and handling precautions.
- As with all fluoropolymer materials, handling and processing should only be carried out in well ventilated areas. Vapor extractor units should be installed above processing equipment. Fumes must not be inhaled and eye and skin contact ought to be avoided. In case of skin contact wash with soap and water. In case of eye contact flush with water immediately and seek medical help. Do not smoke in areas contaminated with powder, vapor or fumes.
- See Material Safety Data Sheet for detailed advice on waste disposal methods.

Packaging

- Hyflon® PFA P7010 is packaged in 10kg non returnable drums. Each drum has two bags liner made of polyethylene resin.
-

Notes

Typical properties: these are not to be construed as specifications.

¹ Laser Diffraction

Hyflon® PFA P7010

perfluoroalkoxy



www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.