

# Kalix® 2855

## high performance polyamide

Kalix® 2855 is a bio-sourced, polyamide-based compound with 55% by weight glass fiber reinforcement. This material is formulated to provide maximum strength, stiffness, impact resistance, and post-mold dimensional stability in thermoplastic parts. Its low viscosity and excellent

flow properties make the material ideal for filling parts with thin-walled sections such as those encountered in the mobile electronics industry.

- Black: Kalix® 2855 BK 000
- White: Kalix® 2855 WH 000

### General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• North America
Filler / Reinforcement	• Glass Fiber	
Features	<ul style="list-style-type: none"> <li>• Good Dimensional Stability</li> <li>• Good Impact Resistance</li> <li>• Good Surface Finish</li> <li>• High Flow</li> <li>• High Stiffness</li> <li>• High Strength</li> </ul>	<ul style="list-style-type: none"> <li>• Hot Water Moldability</li> <li>• Low Moisture Absorption</li> <li>• Low Warpage</li> <li>• Paintable</li> <li>• Platable</li> </ul>
Uses	<ul style="list-style-type: none"> <li>• Cell Phones</li> <li>• Electrical Parts</li> </ul>	<ul style="list-style-type: none"> <li>• Electrical/Electronic Applications</li> <li>• Thin-walled Parts</li> </ul>
RoHS Compliance	• RoHS Compliant	
Appearance	• Black	• White
Forms	• Pellets	
Processing Method	• Injection Molding	• Water-Heated Mold Injection Molding

Physical	Typical Value	Unit	Test method
Specific Gravity	1.55		
Molding Shrinkage			Internal Method
Flow	0.15	%	
Across Flow	0.58	%	
Water Absorption (24 hr, 23°C)	0.090	%	ASTM D570

Mechanical	Typical Value	Unit	Test method
Tensile Modulus	19000	MPa	ISO 527-1
Tensile Stress (Yield)	230	MPa	ISO 527-2
Tensile Strain (Break)	3.8	%	ISO 527-2
Flexural Modulus	17000	MPa	ISO 178
Flexural Stress	355	MPa	ISO 178
Flexural Elongation (Break)	3.9	%	

# Kalix® 2855

## high performance polyamide

---

Impact	Typical Value	Unit	Test method
Notched Izod Impact Strength	20	kJ/m <sup>2</sup>	ISO 180/1A
Unnotched Izod Impact Strength	95	kJ/m <sup>2</sup>	ISO 180

Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	222	°C	ISO 75-2/B
1.8 MPa, Unannealed	213	°C	ISO 75-2/A
Glass Transition Temperature	55.0	°C	ASTM D3418

Electrical	Typical Value	Unit	Test method
Dielectric Constant <sup>1</sup> (2.40 GHz)	3.77		ASTM D2520
Dissipation Factor <sup>1</sup> (2.40 GHz)	0.013		ASTM D2520

### Additional Information

---

Typical values shown tested on Dry as Molded samples.

#### Standard Packaging and Labeling:

- Kalix® HPPA resin is packaged in foil lined, multiwall paper bags containing 25 kg (55 pounds) of material. Individual packages will be plainly marked with the product number, the color, the lot number, and the net weight.

Injection	Typical Value	Unit
Drying Temperature	80	°C
Drying Time	4.0 to 12	hr
Suggested Max Moisture	0.090	%
Rear Temperature	265 to 300	°C
Middle Temperature	280 to 330	°C
Front Temperature	280 to 330	°C
Processing (Melt) Temp	280 to 330	°C
Mold Temperature	80 to 130	°C

# Kalix® 2855

## high performance polyamide

---

### Injection Notes

---

#### Storage:

- Kalix® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Kalix® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Kalix® processing guide.

#### Drying:

- Kalix® HPPA is supplied in sealed bags. It should be dried before molding because excessive moisture content will result in reduced mechanical properties and processing issues, such as excessive nozzle drooling, foaming and splay visible on the molded parts.
- Use of a desiccant dryer with -40°C dewpoint is strongly suggested to ensure Kalix® material has reached optimum moisture content before processing

#### Injection Molding:

- Set injection pressure to give rapid injection. Adjust holding pressure to one-half injection pressure. Set hold time to maximize part weight. Transfer from injection to hold pressure at the screw position just before the part is completely filled.
  - For light colors use lower melt temperature if possible. If operating in the 330°C melt temperature range, keep residence times below 5 minutes.
- 

## Notes

---

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Method B

---

## [www.syensqo.com](http://www.syensqo.com)

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.

