

Radel® R-5600

polyphenylsulfone

Radel® R-5600 is a very high melt flow grade of Radel® polyphenylsulfone (PPSU). It is especially well-suited for parts requiring long flow length with thin walls. Radel® resins offer exceptional hydrolytic stability and toughness superior to other commercially-available, high-temperature engineering resins. They also offer high deflection temperatures and outstanding resistance to environmental stress cracking. Radel® polymers are inherently flame retardant, provide excellent

thermal stability and possess good electrical properties.

Additional Radel® grades include a transparent injection molding grade (R-5000), an opaque, general purpose, injection molding grade (R-5100) and a transparent, extrusion grade (R-5500).

- Natural/Transparent: Radel® R-5600 NT
- Additional Made-to-Order Colors Available

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Features	• Acid Resistant • Base Resistant • Chemical Resistant • Flame Retardant • Good Thermal Stability	• High ESCR (Stress Crack Resist.) • High Heat Resistance • Hydrolytically Stable • Steam Sterilizable • Ultra High Toughness
Uses	• Aerospace Applications • Aircraft Applications	• Food Service Applications
RoHS Compliance	• Contact Manufacturer	
Appearance	• Clear Amber • Clear/Transparent	• Colors Available
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.29		ASTM D792
Melt Mass-Flow Rate (MFR) (365°C/5.0 kg)	34 to 40	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.70	%	ASTM D955
Water Absorption			ASTM D570
24 hr	0.37	%	
Equilibrium	1.1	%	

Radel® R-5600

polyphenylsulfone

Mechanical	Typical Value	Unit	Test method
Tensile Modulus (3.18 mm)	2340	MPa	ASTM D638
Tensile Strength (3.18 mm)	70.3	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield, 3.18 mm	7.2	%	
Break, 3.18 mm	60 to 120	%	
Flexural Modulus (3.18 mm)	2340	MPa	ASTM D790
Flexural Strength (5.0% Strain, 3.18 mm)	91.0	MPa	ASTM D790
Impact	Typical Value	Unit	Test method
Notched Izod Impact (3.18 mm)	690	J/m	ASTM D256
Tensile Impact Strength (3.18 mm)	399	kJ/m ²	ASTM D1822
Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed, 3.18 mm	207	°C	
Glass Transition Temperature ¹	220	°C	DSC
CLTE – Flow (3.18 mm)	5.6E-5	cm/cm/°C	ASTM D696
Electrical	Typical Value	Unit	Test method
Volume Resistivity (3.18 mm)	9.0E+15	ohms·cm	ASTM D257
Dielectric Strength			ASTM D149
0.0254 mm	> 200	kV/mm	
3.18 mm	15	kV/mm	
Dielectric Constant (3.18 mm, 60 Hz)	3.44		ASTM D150
Flammability	Typical Value	Unit	Test method
Flame Rating ² (0.76 mm)	V-0		UL 94
Optical	Typical Value	Unit	Test method
Refractive Index	1.672		ASTM D542
Additional Information	Typical Value	Unit	
Steam Sterilization – w/ Morpholine ³	> 1000	Cycles	
Injection	Typical Value	Unit	
Drying Temperature	149	°C	
Drying Time	2.5	hr	
Processing (Melt) Temp	360 to 391	°C	
Mold Temperature	138 to 163	°C	
Screw Compression Ratio	2.2:1.0		
Extrusion	Typical Value	Unit	
Drying Temperature	171	°C	
Drying Time	4.0	hr	

Radel® R-5600

polyphenylsulfone

Notes

Typical properties: these are not to be construed as specifications.

¹ Heating rate of 36°F (20°C) per minute.

² These flammability ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.

³ Cycles passed without cracking, crazing, or rupture.

Steam Autoclave Conditions:

- Temperature: 270°F (132°C)
- Time: 30 minutes/cycle
- Steam Pressure: 27 psig (0.19 MPa)
- Stress Level: 1000 psi (7.0 MPa) in flexure
- Additive: Morpholine at 50 ppm

www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.

