

Ryton® QA281N

polyphenylene sulfide

Ryton® QA281N (granular powder) polyphenylene sulfide exhibits excellent thermal stability and chemical resistance.

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Features	• Chemical Resistant	• Good Thermal Stability
Uses	• Compounding	
RoHS Compliance	• RoHS Compliant	
Appearance	• Natural Color	
Forms	• Powder	

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.35		ASTM D792
Melt Mass-Flow Rate (MFR) ¹ (316°C/5.0 kg)	700	g/10 min	ASTM D1238
Water Absorption (24 hr, 23°C)	0.050	%	ASTM D570
Ash Content	0.10	wt%	ISO 3451-1
Volatiles (150°C)	< 0.30	wt%	

Thermal	Typical Value	Unit	Test method
Glass Transition Temperature	90.0	°C	ISO 11357-2
Melting Temperature	285	°C	ISO 11357-3

Notes

Typical properties: these are not to be construed as specifications.

¹ Procedure B

Ryton® QA281N

polyphenylene sulfide



www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.