

# Ryton® QC200N polyphenylene sulfide

Ryton® PPS Fiber Grade Resins are high molecular weight polyphenylene sulfide polymers suitable for monofilament and/or multifilament fiber extrusion.

They exhibit excellent thermal stability and chemical resistance.

### General

Material Status	<ul> <li>Commercial: Active</li> </ul>			
Availability	<ul> <li>Asia Pacific</li> </ul>	• Latin America		
Availability	• Europe	• N	North America	
Features	<ul><li>Chemical Resistant</li><li>Good Thermal Stability</li></ul>	High Molecular Weight		eight
Uses	• Fibers			
RoHS Compliance	<ul> <li>RoHS Compliant</li> </ul>			
Forms	<ul> <li>Powder</li> </ul>			
Processing Method	Filament Extrusion			
Physical		Typical Value	Unit	Test method
Density / Specific Gravity		1.35		ASTM D792
Melt Mass-Flow Rate (MFR) (316°C/5.0 kg)		100	g/10 min	ASTM D1238
Water Absorption (Equilibriu	um)	0.050	%	ASTM D570
Ash Content		0.30	wt%	ISO 3451-1
Volatiles (150°C)		< 0.30	wt%	
Mechanical		Typical Value		Test method
Tensile Strength			MPa	ASTM D638
Tensile Elongation (Break)		10	%	ASTM D638
Thermal		Typical Value	Unit	Test method
Deflection Temperature Und	der Load			ASTM D648
1.8 MPa, Unannealed		105	°C	
Melting Temperature		285	°C	ISO 11357-3
CLTE - Flow (-50 to 50°C)		5.0E-5	cm/cm/°C	ASTM E831
Electrical		Typical Value	Unit	Test method
Volume Resistivity		1.0E+16	ohms·cm	ASTM D257
Dielectric Strength		24	kV/mm	ASTM D149
Dielectric Constant (25°C, 1 MHz)		3.20		ASTM D150
Dissipation Factor (25°C, 1 MHz)		2.0E-3		ASTM D150
Optical		Typical Value	Unit	
Color L - Hunter		90.00		

## Ryton° QC200N polyphenylene sulfide

**Additional Information** 

Typical Value Unit

Weight Loss on Heating (300°C)

< 0.50 wt%

### **Notes**

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Procedure B

### www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

respective owners.

© 2024 2023 Syensqo. All rights reserved.

