

Ryton® R-4-220BL

polyphenylene sulfide

Ryton® R-4-220NA and R-4-220BL 40% glass fiber reinforced polyphenylene sulfide compounds provide enhanced mechanical strength after

constant or repeated exposure to high temperature water.

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight	
Features	• Good Strength	
Uses	• Automotive Applications	
RoHS Compliance	• RoHS Compliant	
Automotive Specifications	• CHRYSLER MS-DB-570 CPN3502 Color: Black • FORD WSL-M4D807-A	• GM GMP.PPS.001
Appearance	• Black	
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.68		ASTM D792
Molding Shrinkage			ISO 294-4
Across Flow : 3.20 mm	0.50	%	
Flow : 3.20 mm	0.20	%	
Water Absorption			
24 hr, 23°C	0.021	%	ISO 62
Saturation, 23°C	0.14	%	Internal Method

Mechanical

	Typical Value	Unit	Test method
Tensile Modulus			ISO 527-2
--	16000	MPa	
-- ¹	16100	MPa	
Tensile Stress			
--	175	MPa	ISO 527-2
--	172	MPa	ASTM D638
-- ¹	176	MPa	ISO 527-2
Tensile Strain (Break)	1.5	%	ISO 527-2 ASTM D638
Flexural Modulus			
--	14500	MPa	ASTM D790
--	14000	MPa	ISO 178

Ryton® R-4-220BL

polyphenylene sulfide

Mechanical	Typical Value	Unit	Test method
Flexural Strength			
--	248	MPa	ASTM D790
--	250	MPa	ISO 178
Compressive Strength	275	MPa	ASTM D695
Poisson's Ratio	0.37		ISO 527

Impact	Typical Value	Unit	Test method
Charpy Notched Impact Strength			ISO 179
--	7.9	kJ/m ²	
-- 1	7.5	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
--	45	kJ/m ²	
-- 1	42	kJ/m ²	
Notched Izod Impact			
3.18 mm	80	J/m	ASTM D256
--	8.0	kJ/m ²	ISO 180/A
Unnotched Izod Impact			
3.18 mm	480	J/m	ASTM D4812
--	30	kJ/m ²	ISO 180

Hardness	Typical Value	Unit	Test method
Rockwell Hardness			ASTM D785
M-Scale	103		
R-Scale	122		

Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed	265	°C	
Melting Temperature	280	°C	ISO 11357-3
CLTE			ASTM E831
Flow : -50 to 50°C	1.5E-5	cm/cm/°C	
Flow : 100 to 200°C	1.5E-5	cm/cm/°C	
Transverse : -50 to 50°C	4.0E-5	cm/cm/°C	
Transverse : 100 to 200°C	8.5E-5	cm/cm/°C	
Thermal Conductivity	0.31	W/m/K	Internal Method
UL Temperature Rating	200 to 220	°C	UL 746B

Electrical	Typical Value	Unit	Test method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+16	ohms-cm	ASTM D257
Dielectric Strength	22	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
25°C, 1 kHz	3.80		
25°C, 1 MHz	3.80		

Ryton® R-4-220BL
polyphenylene sulfide

Electrical	Typical Value	Unit	Test method
Dissipation Factor			ASTM D150
25°C, 1 kHz	2.0E-3		
25°C, 1 MHz	3.0E-3		
Arc Resistance	125	sec	ASTM D495
Comparative Tracking Index (CTI)	175	V	IEC 60112
Comparative Tracking Index (CTI)	PLC 4		UL 746A
Flammability	Typical Value	Unit	Test method
Flame Rating (0.8 mm)	V-0		UL 94
Oxygen Index	45	%	ASTM D2863
Additional Information	Typical Value	Unit	
Hydrolytic Stability ²			
Tensile Strength Retained	> 80	%	
Weight Gain	< 1.0	%	

Notes

Typical properties: these are not to be construed as specifications.

¹ Conditioned data is meant to simulate 23°C 50% RH equilibrium values. Conditioning of specimens was achieved per ISO 1110 by exposing specimens for 11 days, 70°C and 62% RH.

² Test specimens aged 1000 hours in water at 140°C (284°F)



www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.