

Ryton® R-7-121BL

polyphenylene sulfide

Ryton® R-7-121NA and R-7-121BL glass fiber and mineral filled polyphenylene sulfide compounds provide good mechanical strength with good flow

and low maintenance molding using conventional molding equipment.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • Latin America • North America
Filler / Reinforcement	• Glass Fiber \ Mineral
Features	• Good Flow • Good Strength
Uses	• Automotive Applications
RoHS Compliance	• RoHS Compliant
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.95		ASTM D792
Molding Shrinkage			ISO 294-4
Across Flow : 3.20 mm	0.40	%	
Flow : 3.20 mm	0.20	%	
Water Absorption			
24 hr, 23°C	0.016	%	ISO 62
Saturation, 23°C	0.13	%	Internal Method

Mechanical

	Typical Value	Unit	Test method
Tensile Modulus			ISO 527-2
--	19200	MPa	
-- ¹	19600	MPa	
Tensile Stress			
--	125	MPa	ISO 527-2
--	117	MPa	ASTM D638
-- ¹	128	MPa	ISO 527-2
Tensile Strain			
Break	0.90	%	ISO 527-2 ASTM D638
Break ¹	1.1	%	ISO 527-2
Flexural Modulus			
--	18000	MPa	ISO 178
--	17200	MPa	ASTM D790

Ryton® R-7-121BL

polyphenylene sulfide

Mechanical	Typical Value	Unit	Test method
Flexural Stress			
--	195	MPa	ISO 178
--	200	MPa	ASTM D790
Compressive Strength	285	MPa	ASTM D695
Poisson's Ratio	0.36		ISO 527
Impact	Typical Value	Unit	Test method
Charpy Notched Impact Strength			ISO 179
--	5.1	kJ/m ²	
-- 1	6.0	kJ/m ²	
Charpy Unnotched Impact Strength	17	kJ/m ²	ISO 179
Notched Izod Impact			
3.18 mm	53	J/m	ASTM D256
--	6.0	kJ/m ²	ISO 180/A
Unnotched Izod Impact			
3.18 mm	210	J/m	ASTM D4812
--	14	kJ/m ²	ISO 180
Hardness	Typical Value	Unit	Test method
Rockwell Hardness			ASTM D785
M-Scale	101		
R-Scale	118		
Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed	265	°C	
Melting Temperature	280	°C	ISO 11357-3
CLTE			ASTM E831
Flow : -50 to 50°C	1.5E-5	cm/cm/°C	
Flow : 100 to 200°C	1.5E-5	cm/cm/°C	
Transverse : -50 to 50°C	3.0E-5	cm/cm/°C	
Transverse : 100 to 200°C	7.0E-5	cm/cm/°C	
Thermal Conductivity	0.58	W/m/K	Internal Method
UL Temperature Rating	220 to 240	°C	UL 746B
Electrical	Typical Value	Unit	Test method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength	18	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
25°C, 1 kHz	4.80		
25°C, 1 MHz	4.90		
Dissipation Factor			ASTM D150
25°C, 1 kHz	4.0E-3		
25°C, 1 MHz	2.0E-3		

Ryton® R-7-121BL
polyphenylene sulfide

Electrical	Typical Value	Unit	Test method
Arc Resistance	185	sec	ASTM D495
Comparative Tracking Index (CTI)	PLC 2		UL 746A
Insulation Resistance ² (90°C)	1.0E+11	ohms	Internal Method

Flammability	Typical Value	Unit	Test method
Flame Rating (0.8 mm)	V-0		UL 94
	5VA		
Oxygen Index	61	%	ASTM D2863

Notes

Typical properties: these are not to be construed as specifications.

¹ Conditioned data is meant to simulate 23°C 50% RH equilibrium values. Conditioning of specimens was achieved per ISO 1110 by exposing specimens for 11 days, 70°C and 62% RH.

² 95%RH, 48 hr



www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.