

Ryton® XE3500BL

polyphenylene sulfide alloy

Ryton® XE3500BL unfilled polyphenylene sulfide alloy compound for extrusion and blow molding

provides excellent mechanical strength, ductility, toughness and chemical resistance.

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Features	• Chemical Resistant • Ductile	• Good Toughness • High Strength
RoHS Compliance	• RoHS Compliant	
Appearance	• Black	
Forms	• Pellets	

Physical	Typical Value	Unit	Test method
Density	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) ¹ (316°C/5.0 kg)	1.0	g/10 min	ASTM D1238
Water Absorption (24 hr, 23°C)	0.10	%	ASTM D570
Mold Shrinkage ²	2.10	%	

Mechanical	Typical Value	Unit	Test method
Tensile Modulus	1600	MPa	ISO 527
Tensile Strength	40.0	MPa	ISO 527
Tensile Elongation (Break)	80	%	ISO 527
Flexural Modulus	1500	MPa	ISO 178
Flexural Strength	60.0	MPa	ISO 178

Impact	Typical Value	Unit	Test method
Notched Izod Impact Strength	60	kJ/m ²	ISO 180/A

Thermal	Typical Value	Unit	Test method
Thermal Conductivity	0.20	W/m/K	ASTM E1530
Coefficient of Linear Thermal Expansion			ISO 11359-2
-50 to 50°C	8.0E-5	cm/cm/°C	
100 to 200°C	1.5E-4	cm/cm/°C	
Heat Deflection Temperature			ASTM D648
0.45 MPa	110	°C	
1.8 MPa	90	°C	

Ryton® XE3500BL
polyphenylene sulfide alloy

Electrical	Typical Value	Unit	Test method
Dielectric Strength	24	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
25°C, 1 kHz	3.10		
25°C, 1 MHz	3.10		
Dissipation Factor			ASTM D150
25°C, 1 kHz	2.0E-3		
25°C, 1 MHz	5.0E-3		
Arc Resistance	120	sec	ASTM D495

Extrusion Notes

Storage:
Bags should be preferably stored in a dry room at a maximum temperature of 60°C (140°F) and should be protected from possible damage.

Pre-Drying:
This resin should be dried prior to extrusion following the recommendations found in the processing guide.

Notes

Typical properties: these are not to be construed as specifications.

¹ Procedure B

² Measured on 102 mm x 102 mm x 3.2 mm plaques, edge gated.



www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.