

Solef® 1015

polyvinylidene fluoride

Solef® 1015 PVDF homopolymer has very high viscosity, suitable for membrane manufacturing. It is available exclusively as powder.

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Features	• Homopolymer	• Ultra High Viscosity
Uses	• Membranes	
Forms	• Powder	

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.75 to 1.80		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/21.6 kg)	2.8 to 4.6	g/10 min	ASTM D1238
Water Absorption (24 hr, 23°C)	< 0.040	%	ASTM D570

Mechanical	Typical Value	Unit	Test method
Tensile Modulus ¹ (23°C, 2.00 mm)	2100 to 2300	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield, 23°C, 2.00 mm	53.0 to 57.0	MPa	
Break, 23°C, 2.00 mm	35.0 to 50.0	MPa	
Tensile Elongation ²			ASTM D638
Yield, 23°C, 2.00 mm	5.0 to 10	%	
Break, 23°C, 2.00 mm	20 to 50	%	

Thermal	Typical Value	Unit	Test method
Glass Transition Temperature	-40.0	°C	ASTM D4065
Melting Temperature	171 to 175	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	137 to 144	°C	ASTM D3418
Crystallization Heat	50.0 to 56.0	J/g	ASTM D3417
Heat of Fusion	57.0 to 66.0	J/g	ASTM D3417

Notes

Typical properties: these are not to be construed as specifications.

¹ Type IV, 1.0 mm/min

² Type IV, 50 mm/min