

# Solef® 42308/0001

## polyvinylidene fluoride

Solef® 42308/0001 PVDF is specifically developed for coextrusion.

### General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Processing Method	• Coextrusion	

Physical	Typical Value	Unit	Test method
Density	1.78	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR)			ASTM D1238
230°C/2.16 kg	6.0 to 8.0	g/10 min	
230°C/5.0 kg	18 to 24	g/10 min	
Water Absorption <sup>1</sup> (24 hr, 23°C)	< 0.040	%	ISO 62

Mechanical	Typical Value	Unit	Test method
Tensile Modulus <sup>2</sup> (23°C)	1900	MPa	ASTM D638
Tensile Strength <sup>3</sup>			ASTM D638
Yield, 23°C	48.0	MPa	
Break, 23°C	30.0	MPa	
Tensile Elongation <sup>3</sup> (Yield, 23°C)	7.0	%	ASTM D638
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.31		
vs. Itself - Static	0.32		
Taber Abrasion Resistance			ISO 5470-1
1000 Cycles, 1000 g, CS-10 Wheel	8.00	mg	

Impact	Typical Value	Unit	Test method
Charpy Notched Impact Strength <sup>4</sup> (23°C)	8.5	kJ/m <sup>2</sup>	ASTM D256

Thermal	Typical Value	Unit	Test method
Melting Temperature	169	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	136	°C	ASTM D3418
Crystallization Heat	52.0	J/g	ASTM D3418
Heat of Fusion <sup>5</sup>	53.0	J/g	ASTM D3418

Electrical	Typical Value	Unit	Test method
Surface Resistivity	> 1.0E+14	ohms	ASTM D257
Volume Resistivity	> 1.0E+14	ohms-cm	ASTM D257

# Solef® 42308/0001

## polyvinylidene fluoride

---

## Notes

---

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Method 1

<sup>2</sup> 1.0 mm/min

<sup>3</sup> 50 mm/min

<sup>4</sup> 4 mm thick, 2 m/s

<sup>5</sup> 80°C to end of melting

---

## [www.syensqo.com](http://www.syensqo.com)

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.

