

Virantage[®] VW-10300 P, FP & SFP polyethersulfone

Virantage® VW-10300 polyethersulfone (PESU) is a non-functionalized, high-temperature sulfone polymer powder. Three grades are offered: Virantage® VW-10300P, Virantage® VW-10300FP, and Virantage® VW-10300SFP providing three particle sizes to meet formulators' specific needs. Their inherent toughness imparts damage tolerance to thermoset composites. Virantage® PESU polymers also offer superior thermal and hydrolytic stability that deliver best-in-class hotwet performance.

These amorphous thermoplastics may be used to toughen a variety of advanced thermoset composites used to produce high-performance aerospace components. Virantage® PESU tougheners have been used successfully in a variety of thermosetting resin systems including epoxies, phenolics and BMIs.

All Virantage® PESU polymers are produced at Syensqo's state-of-the-art, world-scale facility in Panoli, India under ISO 9001:2000 and ISO 14001:2004 certified quality management systems.

Typical Particle Size ~D90

- VW-10300FP 63.0 μm
- VW-10300P 500 μm
- VW-10300SFP 45.0 μm

Material Status	Commercial: Active	
Availability	 Africa & Middle East Asia Pacific Europe 	 Latin America North America
Features	 Amorphous Good Thermal Stability Good Toughness High Heat Resistance 	 Hydrolytically Stable Medium Molecular Weight Medium-high Viscosity
Uses	 Aerospace Applications 	
RoHS Compliance	 Contact Manufacturer 	
Forms	• Powder	
Processing Method	Compounding	

Physical	Typical Value Unit	Test method
Solution Viscosity ¹	800 mPa·s	Internal Method
Moisture - Measured at time of packaging ²	1.0 %	Internal Method
Particle Size ³		
VW-10300FP	63.0 μm	
VW-10300P	500 µm	
VW-10300SFP	45.0 μm	
Residual Solvent - Measured by Gas Chromatography	0.20 %	Internal Method
Thermal	Typical Value Unit	Test method
Glass Transition Temperature	220 °C	DSC

Conoral

Notes

Typical properties: these are not to be construed as specifications. ¹ 25% solution in DMAc at 40°C ² Virantage® PESU is hygroscopic and may absorb moisture in storage. Dry no higher than 130°C for a minimum of 3 hours if needed. ³ Typical Particle Size ~D90 Particle sizes by sieve measurement

www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infinged. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.

