

Xencor™ HPPA LGF-4060

high performance polyamide

Xencor™ HPPA LGF-4060 is a 60% Long Glass Fiber reinforced, easy-flowing, heat stabilized HPPA with a very high flexural modulus. It exhibits unique stiffness/toughness combination, an excellent retention of properties in a wide temperature range, as well as outstanding creep and fatigue resistance.

Xencor™ HPPA LGF-4060 has a pellet length of 9mm and can be processed on most injection-molding machines. It is available in black.

Black: Xencor™ HPPA LGF-4060 BK 000-9

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Long Glass Fiber, 60% Filler by Weight	
Features	• Creep Resistant • Electrically Insulating • Fatigue Resistant • High Impact Resistance • High Temperature Stiffness	• Hot Water Moldability • Low CLTE • Low Shrinkage • Low Warpage
Uses	• Aircraft Applications • Automotive Applications	• Consumer Applications • Industrial Applications
RoHS Compliance	• RoHS Compliant	
Appearance	• Black	
Forms	• Pellets	
Processing Method	• Compression Molding • Injection Molding	• Overmolding

Physical	Dry	Conditioned	Unit	Test method
Density	1.69	--	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	0.10	--	%	Internal Method
Water Absorption (Equilibrium, 23°C, 50% RH)	1.2	--	%	ISO 62

Xencor™ HPPA LGF-4060

high performance polyamide

Mechanical	Dry	Conditioned	Unit	Test method
Tensile Modulus				
23°C	22500	--	MPa	ISO 527-1
23°C	--	21000	MPa	ISO 527-2
70°C	17000	--	MPa	ISO 527-1
Tensile Stress				ISO 527-2
Break, 23°C	285	250	MPa	
Break, 70°C	200	--	MPa	
Tensile Strain (Break)	2.0	2.0	%	ISO 527-2
Flexural Modulus (23°C)	21500	--	MPa	ISO 178
Flexural Stress (23°C)	420	--	MPa	ISO 178

Impact	Dry	Conditioned	Unit	Test method
Charpy Notched Impact Strength				ISO 179
-30°C	60	--	kJ/m ²	
23°C	60	60	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179
-30°C	100	--	kJ/m ²	
23°C	110	100	kJ/m ²	

Thermal	Dry	Conditioned	Unit	Test method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	260	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	255	--	°C	ISO 75-2/A
CLTE - Flow	1.8E-5	--	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.35	--	W/m/K	ISO 22007

Electrical	Dry	Conditioned	Unit	Test method
Electric Strength (2.00 mm)	35	--	kV/mm	IEC 60243-1
Comparative Tracking Index	600	--	V	IEC 60112
Surface Resistivity	1.0E+13	--	ohms/sq	ASTM D257

Additional Information

Conditioned • Conditioned data generated according to test method ISO 1110

Injection	Dry	Unit
Drying Temperature	80	°C
Drying Time	4.0 to 8.0	hr
Suggested Max Moisture	0.10	%
Suggested Max Regrind	20	%
Rear Temperature	290 to 300	°C
Middle Temperature	300	°C
Front Temperature	300	°C
Nozzle Temperature	300	°C
Processing (Melt) Temp	< 320	°C
Mold Temperature	80 to 120	°C

Xencor™ HPPA LGF-4060

high performance polyamide

Injection Notes

Pre-Drying -- Since polyamides are hygroscopic materials as well as sensitive to moisture during processing, this product should always be pre-dried.

Regrind -- Regrind of highly filled thermoplastic materials, such as this material, should only be recycled with special care. The regrind content must never exceed 20% and only regrind of optimum quality should be used. In any case, part properties should be checked.

Notes

Typical properties: these are not to be construed as specifications.

¹ Tested in accordance with S.O.P. methods

www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.

