

Xencor™ PPA LGF-1930 FW HS polyphthalamide

Xencor™ PPA LGF-1930 FW HS is a 30% long glass fiber reinforced, heat stabilized polyphthalamide PPA, with improved friction & wear properties, high heat deflection temperature, very high flexural modulus and low moisture absorption. It displays an excellent retention of properties in a wide temperature range as well as outstanding creep and fatigue resistance.

Xencor™ PPA LGF-1930 FW HS has a pellet length of 9mm and can be processed on most injection-molding machine.

- Black: Xencor™ PPA LGF-1930 FW HS BK 545-9

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Long Glass Fiber, 30% Filler by Weight	
Features	• Creep Resistant • Electrically Insulating • Fatigue Resistant • High Impact Resistance • High Temperature Stiffness	• Low CLTE • Low Friction • Low Shrinkage • Low Warpage
Uses	• Aircraft Applications • Automotive Applications • Consumer Applications	• Gears • Industrial Applications
RoHS Compliance	• RoHS Compliant	
Appearance	• Black	
Forms	• Pellets	
Processing Method	• Compression Molding • Injection Molding	• Overmolding

Physical	Dry	Conditioned	Unit	Test method
Density	1.55	--	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	0.35	--	%	Internal Method
Water Absorption (Equilibrium, 23°C, 50% RH)	1.4	--	%	ISO 62

Mechanical	Dry	Conditioned	Unit	Test method
Tensile Modulus				ISO 527-1
23°C	12000	11500	MPa	
90°C	11000	--	MPa	
120°C	9500	--	MPa	

Xencor™ PPA LGF-1930 FW HS

polyphthalamide

Mechanical	Dry	Conditioned	Unit	Test method
Tensile Stress				ISO 527-2
Break, 23°C	205	195	MPa	
Break, 90°C	160	--	MPa	
Break, 120°C	135	--	MPa	
Tensile Strain (Break)	2.0	2.0	%	ISO 527-2
Flexural Modulus (23°C)	11200	17100	MPa	ISO 178
Flexural Stress (23°C)	290	--	MPa	ISO 178
Coefficient of Friction				ASTM D3702
Dynamic	0.22	--		
Static	0.18	--		
Wear Factor	15	--	10 ⁻⁸ mm ³ /N·m	ASTM D3702

Impact	Dry	Conditioned	Unit	Test method
Charpy Notched Impact Strength (23°C)	12	--	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	65	--	kJ/m ²	ISO 179

Thermal	Dry	Conditioned	Unit	Test method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	300	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	285	--	°C	ISO 75-2/A
CLTE - Flow	2.5E-5	--	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.30	--	W/m/K	ISO 22007

Electrical	Dry	Conditioned	Unit	Test method
Electric Strength (2.00 mm)	35	--	kV/mm	IEC 60243-1
Comparative Tracking Index	550	--	V	IEC 60112
Surface Resistivity	1.0E+12	--	ohms/sq	ASTM D257

Injection	Dry	Unit
Drying Temperature	120	°C
Drying Time	4.0 to 8.0	hr
Suggested Max Moisture	0.030 to 0.060	%
Suggested Max Regrind	20	%
Rear Temperature	330 to 340	°C
Middle Temperature	335	°C
Front Temperature	335	°C
Nozzle Temperature	335 to 340	°C
Processing (Melt) Temp	< 340	°C
Mold Temperature	135 to 160	°C

Xencor™ PPA LGF-1930 FW HS polyphthalamide

Injection Notes

Pre-Drying -- Since polyamides are hygroscopic materials as well as sensitive to moisture during processing, this product should always be pre-dried.

Regrind -- Regrind of highly filled thermoplastic materials, such as this material, should only be recycled with special care. The regrind content must never exceed 20% and only regrind of optimum quality should be used. In any case, part properties should be checked.

Notes

Typical properties: these are not to be construed as specifications.

¹ Tested in accordance with S.O.P. methods

www.syensqo.com

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Syensqo nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Syensqo's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Syensqo's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Syensqo or their respective owners.

© 2024 2023 Syensqo. All rights reserved.

